

DATA SHEET

Version: 01. June 2018



Height-adjustment platelets NR-SBR

Based on a rubber sheet

- Self-adhesive design
- Solvent-free acrylic adhesive
- Adhesive with good final adhesion, suitable for use on construction sites

Applications

- ▶ Double floor construction

Technical data

Substrate: NR/SBR (natural rubber/styrene butadiene rubber) 0.5 to 2.0 mm

Specific weight: 1.26 +/- 0.02 g/cm³ (DIN 53479)

Hardness: 65 +/- 5 Shore A (DIN 53505)

Tensile strength: min. 10 N/mm² (DIN 53504)

Elongation at break: min. 400% (DIN 53504)

Heat resistance: min. -40°C to max. + 60°C

Adhesive: **Synthetic resin acrylate, electrically conductive**

Thickness of adhesive: 0.090 mm +/- 0.01 mm

Electrical conductivity:
(on aluminium 99.5% 0.2 mm) Volume resistance < 10⁵ ohm

Adhesive strength on steel: min. 20 N/25 mm (AFERA 5001)

Peel force based on FTM3: min. 500 mN/50 mm

Heat resistance: -40°C to +90°C

Backing paper: Silicone coated paper

Delivery standard

Cut sheets, tapes and punched parts, depending on the customer's requirements.
Other material thicknesses and adhesive coatings also available.

The above values are intended as a guide or have been obtained under laboratory conditions and do not constitute any guarantee of product properties. We recommend carrying out preliminary tests to check that our products are suitable for use with other products. Under our General Terms and Conditions, we guarantee consistently high product quality, but due to the many possible applications we cannot accept any liability for specific results in practical applications. This data sheet supersedes any previous versions.